

STORK

Stork Herron Testing Laboratories

Material Technology

ABT, Inc.
 PO Box 837
 259 Murdock Road
 Troutman, NC 28166
www.abtdrains.com

1200 WESTINGHOUSE BLVD., SUITE A
 CHARLOTTE, NC 28273
 USA
 TELEPHONE : (704) 588-1131
 TELEFAX : (704) 588-5412
 WEBSITE : www.storkherron.com

P.O. NO.: Verbal

W/O NO.: ABT002-07-20-15486-1

DATE TESTED: 7/28/2006
 ABT PART NUMBER: 1200.MDA
 PART DESCRIPTION: MD200 Series Grate - U.S. Source
 PART DIMENSIONS: 9.38 in W x 19.57 in L x 1.07 in H
 TRENCH WIDTH: 8 in
 TEST PROCEDURE: AASHTO M306-04 with trench width compensation
 TEST BLOCK DIMENSIONS: 6 in Wide x 9 in Long x 1 in Thick (54 in²)
 TEST BLOCK LOCATION: Centered on the top surface of the grate
 BUFFER MATERIAL: 7/8 in thick oriented strand board (same dimension as test block)
 SETTLING LOAD: 50% of proof load, remove load, zero deflection setting
 PROOF LOAD TEST: Load for 60 sec., remove, measure permanent deflection, inspect for cracks
 APPROVAL CRITERIA: Maximum permanent deflection of 0.125 in and no cracks at proof load

SAMPLE NUMBER	PROOF LOAD (LBS)	EQUIVALENT PRESSURE (PSI)	PERMANENT DEFLECTION (in)	ULTIMATE FAILURE LOAD (LBS)	EQUIVALENT PRESSURE (PSI)	TEST RESULTS (PASS/FAIL)
1	27,000	500	0.014	45,200	837	PASS
2	27,000	500	0.026	45,800	848	PASS
3	27,000	500	0.093	42,400	785	PASS

Information and statements in this report are derived from material, information and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of the material tested or analyzed for any particular purpose or use. The samples tested on this certification are certified only for the testing performed. This report is the confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without written approval of this laboratory. The recording of false, fictitious or fraudulent statements or entries on this document may be punished as a felony under Federal Statutes including Federal Law Title 18, Chapter 47. Sample remnants are held for a minimum of 30 days following issuance of test results, at which point they will be discarded unless notified in writing by the client.

Respectfully Submitted



Sam Jackins
 General Manager