

11/28/2006

Material Testing and Non-Destructive Testing

ABT, INC.
PO BOX 837
259 MURDOCK ROAD
TROUTMAN NC 28166

1200 Westinghouse Blvd., Suite A
Charlotte, NC 28273
USA

Telephone : (704) 588-1131
Telefax : (704) 588-5412
Website : www.storkherron.com

Date Received: 11/6/2006

P.O. No.: Verbal

W/O No.: ABT002-11-06-17608-14

Date Tested: 11-13-06
ABT Part No.: 1503.14
Part Description: Heavy Duty Slotted Grade for TF-14
Part Dimensions: 14 W x 18 L x 1.50 H
Trench Width: 12 in
Test Procedure: Modified AASHTO M306-04 with trench width compensation
Test Block Dimensions: 9 x 9
Test Block Location: Centered on the top surface of the grate
Buffer Material: 7/8 in thick oriented strand board (same dimension as test block)
Settling Load: 50% of proof load, remove load, zero deflection setting
Proof Load Test: Load for 60 sec., remove, measure permanent deflection, inspect for cracks
Approval Criteria: Maximum permanent deflection of 5% of trench width and no cracks at proof load

COMPRESSION TEST


Sample Number	Proof Load (LBS)	Equivalent Pressure (PSI)	Permanent Deflection (in)	Ultimate Failure Load (LBS)	Equivalent Pressure (PSI)	Test Results
1	48,600	600	-.0160	200,000*	2,469	Pass
2	48,600	600	-.0175	200,000*	2,469	Pass

*Testing was stopped at 200,000 lbs. pressure.

The tests listed on this certification have been performed in accordance with Customer Requirements and all tests conform.

Information and statements in this report are derived from material, information and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of the material tested or analyzed for any particular purpose or use. The analysis reported on this certification has been performed in accordance with QAM 4th Edition Rev. 0 Dated 2/22/06 and related procedures. The samples tested on this certification are certified only for the testing performed. This report is the confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without written approval of this laboratory. The recording of false, fictitious or fraudulent statements or entries on this document may be punished as a felony under Federal Statutes including Federal Law Title 18, Chapter 47. Sample remnants are held for a minimum of 30 days following issuance of test results, at which point they will be discarded unless notified in writing by the client.

Respectfully Submitted


Sam Jackins
General Manager